

Silirub+ S8800

Revision: 25/06/2021

Page 1 from 3

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation	5 min → 10 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	20 ± 5 Shore A
Density	1,03 g/ml
Elastic recovery (ISO 7389)**	> 80 %
Maximum allowed distortion (ISO 11600)	25 %
Max. tension (ISO 37)**	1,50 N/mm ²
Elasticity modulus 100% (ISO 37)**	0,30 N/mm ²
Elongation at break (ISO 37)**	> 800 %
Temperature resistance**	-60 °C → 180 °C
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Silirub+ S8800 is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties

- No staining on porous surfaces such as marble, granite and other natural stones
- No hydrophobic effect on natural stone.
- Very low emission, EC1+ certified
- Very easy to apply
- No filamenting - can be shaped and finished very well
- Weatherproof
- Permanently elastic after curing
- Neutral curing
- UV-resistant
- Impervious to mould, contains biocide with fungicidal action
- Excellent adhesion on glass, ceramic, enamel and galvanised metals
- 25% maximum allowed distortion
- Solvent, halogen, acid and isocyanate free.
- Resistant against usual household cleaners and disinfectants
- MEKO free

Applications

- Sealing applications on natural stone such as marble, granite, etc. In sanitary areas and kitchens.
- Joints between facade elements, window and doorsills, kitchen worktops etc. of natural stone in general construction applications.

Packaging

Colour: transparent, white, black, joint grey, manhattan, anthracite, jasmine, dust grey, medium grey, transparent-grey, bright beige, marblegrey, bahamabeige, other colors on request

Packaging: 300 ml cartridge

Shelf life

15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: Specially developed for use on natural stone (marble, granite, blue stone, etc..), all usual building substrates, ceramic tiles, aluminium, metals, enamel, glass, ...

Nature: rigid, clean, dry, free of dust and

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub+ S8800

Revision: 25/06/2021

Page 2 from 3

grease.

Surface preparation: Porous surfaces should be primed with Primer 150. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet).

While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding or sealing.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Avoid drying in of Finishing Liquid on the sealant surface or adjacent materials. After sufficient skinning of the sealant rinse Finishing Liquid away with clean water.

Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainings will stimulate the development of fungi.
- A total absence of UV can cause a color change of the sealant.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour.
- When applying, make sure not to spill any sealant on the surface of materials. Taping the surface around the joint can prevent this.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.
- Do not use in applications where continuous water immersion is possible.
- Do not use on polycarbonate. Use Silirub PC instead.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

Standards and certificates

- Conform to ISO 11600 F+G 25LM
- DIN 18545 - 2
- Tested according to ISO 16938-1 (Testing for staining on natural stone by sealants).

Environmental clauses

Leed regulation:

Silirub+ S8800 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub+ S8800

Revision: 25/06/2021

Page 3 from 3

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.